



10/17/00

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

OLIFF & BERRIDGE, PLC
P.O. Box 19928
Alexandria, Virginia 22320
Telephone: (703) 836-6400
Facsimile: (703) 836-2787

NONPROVISIONAL PATENT APPLICATION

Attorney Docket No.: 107615

Date: October 17, 2000

BOX PATENT APPLICATION

NONPROVISIONAL APPLICATION TRANSMITTAL
RULE §1.53(b)

Director of the U.S. Patent and Trademark Office
Washington, D.C. 20231

Sir:

Transmitted herewith for filing under 37 C.F.R. §1.53(b) is the nonprovisional patent application

For (Title): A METHOD OF HOT MARKING, AND A MULTILAYER STRUCTURE FOR
IMPLEMENTING SUCH A METHOD

By (Inventors): Alain BETHUNE

- ☒ Formal drawings (Figs. 1-4; 1 sheets) are attached.
☐ A Declaration and Power of Attorney is filed herewith.
☐ An assignment of the invention to _____ is filed herewith.
☒ An Information Disclosure Statement is filed herewith.
☐ Entitlement to small entity status is hereby asserted.
☐ A Preliminary Amendment is filed herewith.
☐ Please amend the specification by inserting before the first line the sentence --This nonprovisional application claims the benefit of U.S. Provisional Application No. _____, filed _____.
☒ Priority of foreign application(s) No. 99 13228 filed October 22, 1999 in France, is claimed (35 U.S.C. §119).
☒ A certified copy of the above corresponding foreign application(s) is filed herewith.
☒ The filing fee is calculated below:

CLAIMS IN THE APPLICATION AFTER ENTRY OF
ANY PRELIMINARY AMENDMENT NOTED ABOVE

FOR:	NO. FILED	NO. EXTRA
BASIC FEE		
TOTAL CLAIMS	20 - 20	= 0
INDEP CLAIMS	2 - 3	= 0
<input type="checkbox"/> MULTIPLE DEPENDENT CLAIMS PRESENTED		

* If the difference is less than zero, enter "0".

SMALL ENTITY

RATE	FEE
	\$ 355
x 9 =	\$
x 40 =	\$
+ 135 =	\$
TOTAL	\$

OR

OTHER THAN A
SMALL ENTITY

RATE	FEE
	\$ 710
x 18	\$
x 80	\$
+ 270	\$
TOTAL	\$ 710

- ☒ Check No. 112831 in the amount of \$710 to cover the filing fee is attached. Except as otherwise noted herein, the Director is hereby authorized to charge any other fees that may be required to complete this filing, or to credit any overpayment, to Deposit Account No. 15-0461. Two duplicate copies of this sheet are attached.

Respectfully submitted,

William P. Berridge
Registration No. 30,024

Thomas J. Pardini
Registration No. 30,411

WPB:TJP/ka

Inventor Information

Inventor One Given Name:: Alain
Family Name:: BETHUNE
Name Suffix::
City of Residence:: Savigny
State or Prov. of Residence::
Country of Residence:: FRANCE
Inventor Two Given Name::
Family Name::
Name Suffix::
City of Residence::
State or Prov. of Residence::
Country of Residence::
Inventor Three Given Name::
Family Name::
Name Suffix::
City of Residence::
State or Prov. of Residence::
Country of Residence::
Inventor Four Given Name::
Family Name::
Name Suffix::
City of Residence::
State or Prov. of Residence::
Country of Residence::
Inventor Five Given Name ::
Family Name::
Name Suffix::
City of Residence::
State or Prov. of Residence::
Country of Residence::

Correspondence Information

Name Line One:: Oliff & Berridge PLC
Address Line One:: P.O. Box 19928
City:: Alexandria
State or Province:: VA
Postal or Zip Code:: 22320
Telephone:: (703) 836-6400
Fax:: (703) 836-2787
Electronic Mail:: commcenter@oliff.com

Application Information

Title Line One:: A METHOD OF HOT MARKING, AND A
Title Line Two:: MULTILAYER STRUCTURE FOR IMPEMETING
Title Line Three:: SUCH A METHOD
Title Line Four::

09562961.101700

Total Drawing Sheets:: 1
Docket Number:: 107615

Continuity Information

>This application is a::
Application One::
Filing Date::
Patent Number::
which is a::
>>Application Two::
Filing Date::
Patent Number::

Prior Foreign Applications

Foreign Application One:: 99 13228
Filing Date:: October 22, 1999
Country:: FRANCE
Priority Claimed:: Yes
Foreign Application Two::
Filing Date::
Country::
Priority Claimed::
Foreign Application Three::
Filing Date::
Country::
Priority Claimed::

A METHOD OF HOT MARKING, AND A MULTILAYER STRUCTURE FOR IMPLEMENTING SUCH A METHOD

The present invention relates to applying decoration on an article of plastics or other material, and to a
5 method of hot marking.

BACKGROUND OF THE INVENTION

Such a method consists in bringing the article into contact with a multilayer structure having one or more transferrable layers carried by a backing layer, and in
10 applying pressure and heat locally to the structure by means of a gilding iron.

European patent application EP-A-0 668 670 refers to that method in its introduction.

In a later step, the layers transferred onto the
15 article are usually covered in varnish in order to protect the decoration from abrasion.

It is difficult to deposit the varnish exactly on the decoration without spreading any varnish over the article, such that as a general rule the varnish is also
20 present around the decoration, and that can be a drawback from the point of view of appearance.

OBJECTS AND SUMMARY OF THE INVENTION

There exists a need to simplify the making of decoration by a hot marking method and to improve the
25 appearance thereof.

The invention thus provides a novel method of hot marking enabling decoration to be made on an article, and comprising the steps consisting in:

- supplying a multilayer structure comprising a
30 layer of varnish that hardens under the effect of radiation, a backing layer, and a layer of decoration, the varnish layer being situated between the backing layer and the decoration layer;
- bringing said multilayer structure into contact
35 with the article;
- applying pressure and heat to the backing layer at the location where it is desired to transfer the

09688961.101700

decoration layer onto the article, the varnish layer being such as to be transferred locally onto the article together with the decoration layer;

- withdrawing the backing layer; and
- 5 · causing the layer of varnish that has been transferred onto the article to harden by exposing it to said radiation.

By means of the invention, the decoration can be protected from abrasion without an additional step of
10 depositing varnish.

It is simpler to make the decoration, and its appearance is improved since the varnish which protects the decoration does not extend over the article but only over the layer of decoration deposited on the article.

- 15 The varnish used can be a UV thermal varnish, in particular a cationic UV thermal varnish or a hydroxylated urethane acrylate UV thermal varnish.

The varnish can include oligomers of low molecular weight, preferably lying in the range 800 to 2000, and
20 can contain a solvent prior to being applied on the backing layer.

Advantageously, the varnish includes one or more pigments or dyes.

- 25 Preferably, the varnish includes photo-initiators at a concentration by weight lying in the range 0.3% to 3%, and preferably about 0.5%.

The decoration layer is advantageously coated in a layer of hot-melt adhesive.

- 30 The layer of varnish is preferably exposed to said radiation while its temperature is still close to the maximum temperature it reaches when pressure and heat are applied to the backing layer, the temperature difference preferably being less than 30% of the maximum temperature.

- 35 The decoration layer can be a layer of metal vacuum-deposited on the varnish layer before the varnish layer

09688961 " 101700

has been exposed to the radiation that causes cross-linking therein.

In a variant, the decoration layer can be a layer of ink deposited by printing on the varnish layer before the varnish layer has been exposed to said radiation.

The invention also provides a multilayer structure for implementing a hot marking method, the structure comprising a layer of varnish that hardens under the effect of radiation, said varnish being unexposed to said radiation, a backing layer, and a layer of decoration suitable for being transferred locally onto an article by applying heat and pressure to the backing layer.

Advantageously, the decoration layer is covered in a layer of hot-melt adhesive.

Preferably, the varnish used is a UV thermal varnish.

The decoration layer can be a layer of vacuum-deposited metal or a layer of ink deposited by printing.

BRIEF DESCRIPTION OF THE DRAWING

The invention will be better understood on reading the following detailed description of a non-limiting implementation, and on examining the accompanying drawing, in which:

- Figure 1 is a diagrammatic section view of a multilayer structure of the invention;
- Figure 2 is a diagram showing the various steps in fabricating the multilayer structure of Figure 1; and
- Figures 3 and 4 show how decoration can be put on an article.

MORE DETAILED DESCRIPTION

The multilayer structure 10 shown in Figure 1 comprises a backing layer 11 covered on one face 12 by a separation layer 13.

A layer of varnish 14 has one face in contact with the separation layer 13 and on its other face 17 it carries a layer of decoration 15.

The face 18 of the decoration layer 15 facing away from the varnish layer 14 is covered in a layer of adhesive 16.

5 The various layers 11 to 16 are shown in the figures without complying with their real proportions, in order to clarify the drawing.

By way of example, the backing layer 11 can be about 10 micrometers (μm) thick, the separation layer can be about 0.01 μm thick, the varnish layer 14 can be about 1 μm thick, the decoration layer 15 can be about 0.02 μm thick, and the adhesive layer 16 can be about 1 μm thick.

The backing layer 11 can be constituted by a polyester film, for example.

15 The separation layer 13 can be constituted by a covering of wax or of silicone, for example.

The separation layer 13 adheres to the backing layer 11 more strongly than to the varnish layer 14.

By way of example, the varnish layer 14 can be constituted by a cationic UV thermal varnish or by a hydroxylated urethane acrylate UV thermal varnish.

In general, the varnish used can have one or two components with or without a solvent, including oligomers of low molecular weight, preferably lying in the range 800 to 2000, and it can contain one or more pigments or dyes and photo-initiators, where the photo-initiators are preferably at a concentration by weight lying in the range 0.3% to 3%, and preferably about 0.5%.

25 The decoration layer 15 can be constituted by a metal such as aluminum or by ink which is deposited by printing, e.g. by an offset printing process.

The adhesive layer 16 is constituted by a hot-melt adhesive.

In a variant embodiment that is not shown, the multilayer structure also includes, between the varnish layer 14 and the decoration layer 15, a layer of varnish that is colored, e.g. yellow.

To make the multilayer structure 10 and as illustrated in Figure 2, the first step 20 is to unroll the backing layer 11 under a first coating member which deposits the separation layer 13, then the backing layer 11 as treated in this way is brought under a second coating member which deposits, in step 21, the layer of varnish 14 in the non-cross-linked state.

The varnish layer 14 is then heated to a temperature that is sufficient to initiate pre-curing, evaporating any solvent and ensuring that it is dimensionally stable on the backing layer 11.

Thereafter, in step 22, the varnish layer 14 is metallized under a vacuum so as to deposit the aluminum which constitutes the decoration layer 15.

The decoration layer adheres particularly well to the varnish layer, given that the varnish layer has not yet been exposed to UV radiation.

Finally, adhesive is deposited by means of a third coating member so as to make the adhesive layer 16 in step 23.

In the implementation described, the varnish layer 14 is colored throughout, e.g. yellow so as to imitate gold.

The dyes or pigments used for coloring the varnish layer 14 and the photo-initiators contained therein are selected in such a manner as to present absorption peaks at different wavelengths, for example respectively 420 nanometers (nm) and 300 nm.

Thus, the dyes or pigments used do not absorb the UV radiation that serves to cause the varnish to cross-link.

The multilayer structure 10 is used as follows.

It is brought into contact with the outside surface of an article A to be decorated, and a gilding iron F having portions in relief R corresponding to the pattern to be made is used to apply pressure and heat to the outside face of the backing layer 11, as shown in Figure 3.

The pressure and the heat from the gilding iron F are transmitted through the various layers of the multilayer structure 10 to the adhesive layer 16 which attaches to the article A.

5 When the multilayer structure 10 is withdrawn, as shown in Figure 4, the decoration layer 15 remains on the article A at locations where pressure and heat were applied locally.

10 The separation layer 13 facilitates detachment of the varnish layer 14.

The separation layer 13 remains attached to the backing layer 11 when it is withdrawn.

09683961.101700
15 The portions of the decoration layer 15 secured to the article A by the adhesive layer 16 are themselves covered on their outside faces by the varnish layer 14 which is then exposed to short wavelength ultraviolet radiation (UVB) emitted by a source L.

Exposure to the UV radiation causes the varnish to become cross-linked and hardens it.

20 After it has cross-linked, the varnish layer 14 constitutes protection against abrasion and unlike the prior art there is no need subsequently to deposit a layer of protective varnish on the decoration.

It will be observed that the power required from the
25 source L can be relatively low when the decoration layer 15 is a layer of metal since the radiation reflected by said layer of metal into the layer of varnish 14 contributes to activating the photo-initiators.

Thus, the power of the source L can be about
30 100 watts per centimeter (W/cm) for example (where power is measured per unit length of the bulb).

The varnish layer 14 is preferably exposed to the ultraviolet radiation immediately after the backing layer 11 has been withdrawn so as to take advantage of the fact
35 that the varnish is still relatively hot and thus more sensitive to exposure to ultraviolet radiation.

The gilding iron F is used in such a manner as to apply the heat and pressure required for obtaining the desired result, e.g. by being raised to a temperature of about 150°C.

- 5 Where appropriate, the article A can be subjected to surface treatment in order to improve adhesion of the decoration.

0968961-101700

CLAIMS

1/ A hot marking method enabling decoration to be made on an article, the method comprising the steps consisting in:

- 5 · supplying a multilayer structure comprising a layer of varnish that hardens under the effect of radiation, a backing layer, and a layer of decoration, the varnish layer being situated between the backing layer and the decoration layer;
- 10 · bringing said multilayer structure into contact with the article;
- applying pressure and heat to the backing layer at the location where it is desired to transfer the decoration layer onto the article, the varnish layer
- 15 being such as to be transferred locally onto the article together with the decoration layer;
- withdrawing the backing layer; and
- causing the layer of varnish that has been transferred onto the article to harden by exposing it to
- 20 said radiation.

2/ A method according to claim 1, wherein the varnish used is a UV thermal varnish.

- 25 3/ A method according to claim 2, wherein the varnish used is a cationic UV thermal varnish.

- 4/ A method according to claim 2, wherein the varnish used is a hydroxylated urethane acrylate UV thermal
- 30 varnish.

- 5/ A method according to claim 1, wherein the varnish includes oligomers of low molecular weight, preferably lying in the range 800 to 2000.

35

09685961 101700

6/ A method according to claim 1, wherein the varnish contains a solvent prior to being applied to the backing layer.

5 7/ A method according to claim 1, wherein the varnish includes one or more pigments or dyes.

8/ A method according to claim 1, wherein the varnish includes photo-initiators at a concentration by weight
10 that lies preferably in the range 0.3% to 3%, and preferably about 0.5%.

9/ A method according to claim 1, wherein the backing layer is constituted by a polyester film.

15 10/ A method according to claim 1, wherein the decoration layer is covered in a layer of hot-melt adhesive.

11/ A method according to claim 1, wherein the varnish
20 layer is exposed to said radiation while its temperature is still close to its maximum temperature at the moment when pressure and heat are applied to the backing layer, the temperature difference being preferably less than 30% of the maximum temperature.

25 12/ A method according to claim 1, wherein the decoration layer is a layer of metal deposited under a vacuum onto the layer of varnish before the varnish is exposed to said radiation.

30 13/ A method according to claim 1, wherein the decoration layer is a layer of ink deposited by printing on the layer of varnish before the varnish is exposed to said radiation.

35 14/ A multilayer structure for implementing the method as defined in claim 1.

09688961.101700

- 15/ A multilayer structure for implementing a hot marking method, the structure comprising a layer of varnish that hardens under the effect of radiation, said varnish being unexposed to said radiation, a backing layer, and a layer of decoration suitable for being transferred locally onto an article by applying heat and pressure to the backing layer.
- 10 16/ A multilayer structure according to claim 15, wherein the decoration layer is covered in a layer of hot-melt adhesive.
- 15 17/ A multilayer structure according to claim 16, wherein the varnish used is a UV thermal varnish.
- 18/ A multilayer structure according to claim 17, wherein the decoration layer is a layer of vacuum-deposited metal.
- 20 19/ A multilayer structure according to claim 15, wherein the decoration layer is a layer of ink deposited by printing.
- 25 20/ An article having decoration applied thereto by a hot marking method as defined in claim 1.

00688961.101700

A B S T R A C T

The invention relates to a hot marking method enabling decoration to be made on an article, the method comprising the steps consisting in:

- supplying a multilayer structure comprising a layer of varnish that hardens under the effect of radiation, a backing layer, and a layer of decoration, the varnish layer being situated between the backing layer and the decoration layer;
- bringing said multilayer structure into contact with the article;
- applying pressure and heat to the backing layer at the location where it is desired to transfer the decoration layer onto the article, the varnish layer being such as to be transferred locally onto the article together with the decoration layer;
- withdrawing the backing layer; and
- causing the layer of varnish that has been transferred onto the article to harden by exposing it to said radiation.

09688961.101700




FIG. 1



FIG. 2




FIG. 3




FIG. 4